

Magnetism and superconductivity in $\text{CeRh}_{1-x}\text{Ir}_x\text{In}_5$ heavy fermion materials.

G.D. Morris¹, R.H. Heffner¹, J.E. Sonier², D.E. MacLaughlin³, O.O. Bernal⁴, G.J. Nieuwenhuys⁵, A.T. Savici⁶,
P.G. Pagliuso¹ and J.L. Sarrao¹

¹*Los Alamos National Laboratory, MS K764, Los Alamos, NM 87545, USA*

²*Department of Physics, Simon Fraser University, Burnaby, British Columbia V5A 1S6, Canada*

³*Department of Physics, University of California, Riverside, California 92521, USA*

⁴*Physics Department, California State University, Los Angeles, California 90032, USA*

⁵*Kamerlingh Onnes Laboratory, Leiden University, Postbus 9504 - 2300 RA Leiden, The Netherlands*

⁶*Department of Physics, Columbia University, New York, NY 10027, USA*

(February 2, 2008)

We report zero-field μSR studies of cerium based heavy-fermion materials $\text{CeRh}_{1-x}\text{Ir}_x\text{In}_5$. In the superconducting $x=0.75$ and 1 compositions muon spin relaxation functions were found to be temperature independent across T_c ; no evidence for the presence of electronic magnetic moments was observed. The $x=0.5$ material is antiferromagnetic below $T_N=3.75$ K and superconducting below $T_c=0.8$ K. μSR spectra show the gradual onset of damped coherent oscillations characteristic of magnetic order below T_N . At 1.65 K the total oscillating amplitude accounts for at least 85% of the sample volume. No change in precession frequency or amplitude is detected on cooling below T_c , indicating the microscopic coexistence of magnetism and superconductivity in this material.

A tetragonal HoCoGa_5 crystal structure is common to all the CeMIn_5 materials, which may be viewed as alternating layers of CeIn_3 and MIn_2 . Varying fractions of Ir, Rh or Co on the M site results in a rich phase diagram exhibiting antiferromagnetic and superconducting properties. It has been noted [1] that the superconducting transition temperature T_c increases monotonically with c/a , suggesting that the superconductivity is most robust when the layers of CeIn_3 are more isolated. It is not clear whether this reflects a shift toward optimal hybridization, or greater 2D character in a possible magnetic pairing interaction. CeCoIn_5 has the highest $T_c = 2.3$ K of the known heavy fermion superconductors [2]. Specific heat and thermal conductivity measurements on CeCoIn_5 and CeIrIn_5 found power-law temperature dependences, indicating the presence of lines of nodes in their superconducting gaps [3]. These results led to speculation that 2D (or at least anisotropic) AFM fluctuations play an important role in magnetically-mediated heavy-fermion superconductivity within the CeMIn_5 family. Recent theoretical work has also found that quasi-2D magnetic fluctuations result in superconductivity at higher temperatures than 3D fluctuations in metals which are nearly antiferromagnetic [4]. However, neutron scattering experiments on CeRhIn_5 found AFM fluctuations along the c -axis, with a weaker interaction than between Ce moments in-plane, but concluded that magnetic correlations are nonetheless 3D in nature [5]. We have performed μSR experiments on several superconducting compositions of $\text{CeRh}_{1-x}\text{Ir}_x\text{In}_5$, with the objective of elucidating the magnetic and superconducting properties of these materials.

The phase diagram of $\text{CeRh}_{1-x}\text{Ir}_x\text{In}_5$ shows a range of magnetic and superconducting properties which may be tuned with composition or pressure [6]. CeRhIn_5

is known from neutron scattering experiments to have an incommensurate antiferromagnetic order below $T_N=3.8$ K, in which the moments lie in the $a-b$ plane but spiral 107° per unit cell along the c -axis [7]. Superconductivity is present for compositions $0.3 < x < 1$, and there is evidence from macroscopic susceptibility and resistivity measurements that AFM order and superconductivity coexist for $0.3 < x < 0.6$ [1]. A local probe like μSR can address whether the magnetism and superconductivity coexist on a microscopic scale.

Zero-field time-differential μSR spectra were taken on superconducting samples of CeIrIn_5 ($T_c=0.4$ K) and $\text{CeRh}_{0.25}\text{Ir}_{0.75}\text{In}_5$ ($T_c=0.7$ K) with the dilution refrigerator at the TRIUMF M15 channel. Zero magnetic field (ZF) conditions were prepared by quenching the superconducting solenoid in the dilution refrigerator. Residual fields on the order of 1 G were then zeroed to less than 20 mG with external trim coils and a field-zeroing method described elsewhere in these proceedings [8]. Samples were oriented with their c axes nominally parallel to the muon momentum and spin.

A background signal originating from muons stopping in cryostat parts near the sample position was characterized with the entire area of the silver sample stage covered by a GaAs wafer, which produces no decay asymmetry in ZF. In both CeIrIn_5 and $\text{CeRh}_{0.25}\text{Ir}_{0.75}\text{In}_5$ the experimental decay asymmetry followed a slow, static Gaussian Kubo-Toyabe form with temperature-independent relaxation rates Δ across their superconducting transitions, shown in Fig. 1. Average values of Δ in CeIrIn_5 and $\text{CeRh}_{0.25}\text{Ir}_{0.75}\text{In}_5$ were found to be $0.239(4)$ and $0.276(2) \mu\text{s}^{-1}$ respectively. There is thus no evidence of an increased relaxation rate or coherent precession signal which might result from the onset of electronic (spin or orbital) moments at T_c . These results are similar to

those recently published by Higemoto *et.al.* [9] who also found no observable electronic magnetic moment in the superconducting state in CeIrIn₅. Our results differ in that we obtained excellent fits of the polarization to a *static* Kubo-Toyabe relaxation function.

Zero-field experiments were performed on two samples of CeRh_{0.5}Ir_{0.5}In₅ at the LTF ($T \leq 1.15$ K) and GPS ($T \geq 1.65$ K) channels at PSI, Switzerland. Auxiliary experiments found no indications of inhomogeneity in these samples; sharp transitions were found in bulk resistivity and AC susceptibility. μ SR spectra (Fig. 2a) show rapidly-damped, coherent oscillations developing below $T_N=3.75$ K. This component of the signal is clearly not of a Kubo-Toyabe form since the minimum in corrected asymmetry is negative. From T_N down to 2 K the static Gaussian Kubo-Toyabe (G-KT) component diminishes in amplitude, while the oscillating and longitudinal components grow. Above $T=2$ K the experimental asymmetry was fitted to the sum of two oscillating signals, plus the slow G-KT and a longitudinal signal due to that component of the muon spin parallel to the local magnetic field. The total asymmetry remained constant. The G-KT signal vanishes at temperatures of 1.65 K and below. For spectra taken in the dilution refrigerator, a non-relaxing silver background component was also present. Figure 2b shows examples of two spectra at 0.1 and 1.15 K.

Two oscillating components were observed in the first μ s of the CeRh_{0.5}Ir_{0.5}In₅ spectra taken at temperatures below 2.75 K. Total asymmetry of the oscillating components saturated by $T=2$ K. Rapid damping made it impossible to obtain reliable fits to the higher frequency and its relaxation rate, however. The muon site(s) in these materials remain to be determined. Nevertheless, transverse field data in CeIrIn₅ from $T=2-300$ K [10] show that the muon stops in two magnetically inequivalent sites. This is consistent with the two observed oscillating signals in CeRh_{0.5}Ir_{0.5}In₅. High relaxation rates may be the result of a broad field distribution at the muon sites which would result from incommensurate magnetic order similar to that in CeRhIn₅.

The smaller frequency in CeRh_{0.5}Ir_{0.5}In₅ ($\nu_1(T)$ in Fig. 3) is nearly temperature-independent below 1.15 K, with no obvious discontinuity at T_c . The oscillating asymmetry in spectra taken with the muon spin rotated (to 50° from the *c*-axis) amounted to 85% of the full asymmetry so *at least* 85% of the sample volume is magnetic. Spectra were essentially indistinguishable between $T=1.15$ K and 0.050 K, but these spectra have smaller oscillating amplitudes and larger longitudinal amplitudes due to the orientation of the muon spin with respect to the local field. We have therefore normalized the total oscillating fraction measured in spectra for $T \leq 1.15$ K to those measured with rotated spin at $T \geq 1.65$ K. This corrected oscillating fraction is also shown in Fig. 3. Note that no change occurred in the asymmetry or frequency on crossing the superconducting transition - *i.e.*, mag-

netic order persists unchanged into the superconducting state. Susceptibility measurements reveal a diamagnetic signal at T_c that is at least 85% of that expected for full shielding. We, therefore, conclude that superconductivity and AFM order must coexist microscopically in the majority of the sample volume.

In summary, we find no evidence for electronic magnetic moments coincident with the onset of superconductivity in CeIrIn₅ or CeIr_{0.75}Rh_{0.25}In₅. Furthermore, the antiferromagnetism in CeIr_{0.5}Rh_{0.5}In₅ coexists microscopically with superconductivity below T_c .

This work was supported in part by US NSF grants DMR-0102293 (UC Riverside) and DMR-9820631 (CSU Los Angeles). JES acknowledges support from the Natural Sciences and Engineering Research Council (NSERC) and the Canadian Institute for Advanced Research. Work at Los Alamos was performed under the auspices of the U.S. Department of Energy, Office of Science.

-
- [1] P.G. Pagliuso, C. Petrovic, R. Movshovich, D. Hall, M.F. Hundley, J.L. Sarrao, J.D. Thompson, Z. Fisk, Phys. Rev. B 64 (2001) R100503.
 - [2] C. Petrovic, P.G. Pagliuso, M.F. Hundley, R. Movshovich, J.L. Sarrao, J.D. Thompson and Z. Fisk, J. Phys.: Condens. Matter 13 (2001) L337.
 - [3] R. Movshovich, M. Jaime, J.D. Thompson, C. Petrovic, Z. Fisk, P.G. Pagliuso, J.L. Sarrao, Phys. Rev. Lett. 86 (2001) 5152.
 - [4] P. Monthoux and G.G. Lonzarich, Phys. Rev. B 62 (2001) 054529.
 - [5] Wei Bao, G. Aeppli, J.W. Lynn, P.G. Pagliuso, J.L. Sarrao, M.F. Hundley, J.D. Thompson, Z. Fisk, Phys. Rev. B 65 (2002) 100505R.
 - [6] H. Hegger, C. Petrovic, E.G. MoshoPoulou, M.F. Hundley, J.L. Sarrao, Z. Fisk and J.D. Thompson, Phys. Rev. Lett. 84 (2002) 4986.
 - [7] Wei Bao, P.G. Pagliuso, J.L. Sarrao, J.D. Thompson, Z. Fisk, J.W. Lynn, and R.W. Erwin, Phys. Rev. B 62 (2001) R14621; 63 (2001) 219901(E).
 - [8] G.D. Morris and R.H. Heffner, Physica B, these proceedings.
 - [9] Wataru Higemoto, Akihiro Koda, Ryosuke Kadono, Yu Kawasaki, Yoshinori Haga, Dai Aoki, Rikio Settai, Hiroaki Shishido and Yoshichika Onuki, J. Phys. Soc. Japan 71 (2002) 1023.
 - [10] G.D. Morris *et.al.*, in preparation.

FIGURE CAPTIONS

Fig.1 ZF static Gaussian Kubo-Toyabe widths in CeIrIn₅ (squares) and CeRh_{0.25}Ir_{0.75}In₅ (circles) are temperature independent across superconducting transition

temperatures T_c .

Fig.2.(a) Corrected Up-Down asymmetries in $\text{CeRh}_{0.5}\text{Ir}_{0.5}\text{In}_5$ at several temperatures, showing the gradual evolution of the spin relaxation function from a static Gaussian Kubo-Toyabe to oscillating and longitudinal components. The muon spins in these spectra were rotated to approximately 50° from the c axis. (b) Low temperature Back-Forward asymmetries at $T=0.1$ and 1.15 K with muon spins oriented along the c axis. Low temperature spectra taken in the dilution refrigerator are virtually identical.

Fig.3. The temperature dependence of the frequency ν_1 (circles) and total oscillating amplitude (triangles) in two samples of $\text{CeRh}_{0.5}\text{Ir}_{0.5}\text{In}_5$. No change in the relaxation function is seen on crossing into the superconducting state at $T_c=0.8$ K. Filled symbols correspond to sample 1.





